

General Description and Use		
Argotec SKU Number	18450-FR	
Typical application	Die cut and seal	
Polymer	Thermoplastic polyurethane, aromatic polyether	
Extrusion method	Flat die	
Gauge	1.0 - 80 mils (25 - 2000 microns)	
Width	Up to 60 inches (1.52 meters)	
Length	Up to 1000 non-spliced yards (914.4 meters)	
Key attributes	<ul style="list-style-type: none"> ■ Clear finish ■ Soft ether ■ Mid-range softening temperature ■ FAR 25.853A ■ FMVSS-302 	
Typical Properties	Test Method	Value
Durometer	ASTM D-2240	Shore 86A
Tensile stress @ 100% elongation	ASTM D-412	1100 psi 7.6 MPa
Tensile stress @ 300% elongation		1750 psi 12 MPa
Tensile strength		4800 psi 33 MPa
Elongation at break		640%
Tensile set at break		70%
Tear strength	D-624 ¹	600 pli 105 kN/m
Abrasion resistance	D-1044 ²	30 mg loss

¹ Die C.

² Taber abrasion H-18 wheel, 1000 gm weight, 1000 cycles.

Product information revised: July 1, 2014

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.

SWM INTL

53 Silvio O. Conte Drive • Greenfield, Massachusetts 01301 U.S.A.
tel: 413/772-2564 • fax: 413-772-2565 • web: www.swmintl.com • email: ams@swmintl.com

TECHNICAL DATA