

Coretec™ SS-1485

General Description

- Typical application: Tubing
- Polymer: Thermoplastic polyurethane, aromatic polyester
- Packaging: Bulk spools, 100-foot (30.5 m) coils or cut pieces
- Key attributes:
 - Tough, strong
 - Long lasting
 - Kink resistant
 - Abrasion resistant
 - Chemical resistant
 - Wide operating temperature range
 - Easy processing in assembly operations

Physical Property	Test Method	Value
Inside diameter	N/A	1/16" - 1.0" (1.59 - 25.4 mm)
Outside diameter	N/A	1/8" - 1-1/4" (3.17 - 31.8 mm)
Durometer	ASTM D-2240	Shore 85A (+/- 5)
Specific gravity	ASTM D-792	1.20
Modulus @ 100% strain	ASTM D-638	800 psi (5.51 MPa)
Modulus @ 300% strain		1800 psi (12.41 MPa)
Modulus @ break		7000 psi (48.26 MPa)
Modulus of elasticity up to 10% strain		30 psi (0.21 MPa)
Elongation @ break		400%
Set @ break		30%
Tear strength	D-624 ¹	425 pli (74.38 kN/m)
Max continuous service temperature	N/A	-40°F to 225°F (-4°C to 107°C)
Melt point range	N/A	360°F to 400°F (182°C to 204°C)

¹Die C

04.12.21_REV1

Advanced
Materials
& Structures

ams@swmintl.com
swmintl.com

Copyright © Schweitzer-Mauduit International, Inc. (2021). All Rights Reserved. SWM™ and CORETEC™ are trademarks of Schweitzer-Mauduit International, Inc. ("SWM") or an affiliated company of SWM.

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.